



SHERWIN-WILLIAMS®



Paint Maintenance Guide

River District - Parcel 21

Presented To:
Dalvir Singh

Presented By:
Rakesh Johar
Sales Representative

(604) 345-3282
rakesh.johar@sherwin.com

Products are available at:
SURREY-CENTRAL
10120 KING GEORGE BLVD
SURREY, BC V3T2W4
(604) 588-0311

February 07, 2020



SHERWIN-WILLIAMS®

BRITE STAR PAINTING LTD.
February 07, 2020

Description: SOLO Interior/Exterior 100% Acrylic, Semi-Gloss Extra White	Product: A76W00051	Substrate: Wood	Area: Doors, Trims, Elevator Trims
Color: 2305 - Rialto	Label: Finish		

Due to screen and print limitations, colors seen here may not accurately reflect painted colors. To confirm your color choices, visit your neighborhood Sherwin-Williams store

Description: DuraCraft Exterior Acrylic Latex Flat Extra White	Product: C01W00251	Substrate: Other	Area: Exterior
Color: 2133-60 - Sidewalk Gray	Label: Finish		

Due to screen and print limitations, colors seen here may not accurately reflect painted colors. To confirm your color choices, visit your neighborhood Sherwin-Williams store

Description: ProMar® 400 Zero VOC Interior Latex Flat Extra White	Product: B30W04651	Substrate: Drywall	Area: Ceiling
Color: CC-30 - Oxford White	Label: Finish		

Due to screen and print limitations, colors seen here may not accurately reflect painted colors. To confirm your color choices, visit your neighborhood Sherwin-Williams store



SHERWIN-WILLIAMS®

BRITE STAR PAINTING LTD.
February 07, 2020

Description: DuraCraft Exterior Acrylic Latex Satin Extra White	Product: C07W00251	Substrate: Wood	Area: Exterior
Color: 2124-10 - Wrought Iron	Label: Finish		

Due to screen and print limitations, colors seen here may not accurately reflect painted colors. To confirm your color choices, visit your neighborhood Sherwin-Williams store

Description: Property Solutions Interior Latex Eg -Shel White	Product: B20W03050	Substrate: Drywall	Area: Interior Walls
Color: OC-27 - Balboa Mist	Label: Finish		

Due to screen and print limitations, colors seen here may not accurately reflect painted colors. To confirm your color choices, visit your neighborhood Sherwin-Williams store

Description: SOLO Interior/Exterior 100% Acrylic, Semi-Gloss Extra White	Product: A76W00051	Substrate: Wood	Area: Doors, Trims
Color: CC-30 - Oxford White	Label: Finish		

Due to screen and print limitations, colors seen here may not accurately reflect painted colors. To confirm your color choices, visit your neighborhood Sherwin-Williams store



SHERWIN-WILLIAMS®

BRITE STAR PAINTING LTD.
February 07, 2020

Description:
ProMar® 400
Zero VOC
Interior Latex
Low Sheen
Extra White

Product:
B24W04651

Substrate:
Drywall

Area:
Interior Walls

Color:
OC-27 - Balboa
Mist

Label:
Finish

Due to screen and print limitations, colors seen here may not accurately reflect painted colors. To confirm your color choices, visit your neighborhood Sherwin-Williams store

Description:
DuraCraft
Exterior Acrylic
Latex Flat Extra
White

Product:
C01W00251

Substrate:
Wood

Area:
Exterior

Color:
2137-60 - Gray
Owl

Label:
Finish

Due to screen and print limitations, colors seen here may not accurately reflect painted colors. To confirm your color choices, visit your neighborhood Sherwin-Williams store



SHERWIN-WILLIAMS®

BRITE STAR PAINTING LTD.
February 07, 2020

Description:
All Surface
Enamel HP
Semi-Gloss
(Canada) Extra
White

Product:
A41WQ8051

Substrate:
Steel

Area:
Metal service
doors

Color:
P003 2283 -
Gossamer

Label:
Finish

Due to screen and print limitations, colors seen here may not accurately reflect painted colors. To confirm your color choices, visit your neighborhood Sherwin-Williams store



SHERWIN-WILLIAMS®

BRITE STAR PAINTING LTD.
February 07, 2020





SHERWIN-WILLIAMS®

Reference Pages

Data Pages



101.88

SOLO[®]

100% Acrylic Interior/Exterior Semi-Gloss A76 Series

As of 05/11/2016, Complies with:		
OTC	Yes	LEED® 09 NC CI Yes
SCAQMD	Yes	LEED® 09 CS Yes
CARB	Yes	LEED® 09 H & S Yes
CARB SCM 2007	Yes	LEED® v4 Emissions Yes
MPI	Yes	LEED® v4 VOC Yes

CHARACTERISTICS

Solo 100% Acrylic Interior/Exterior Semi-Gloss creates a hard, scrubbable finish that is resistant to burnishing, wearing, and blocking. **Solo Semi-Gloss** is excellent choice for specifications where 100% acrylic interior finishes are required. It is designed for use on doors, trim, walls, & shutters. **Solo Semi-Gloss** can be applied to surfaces with a pH up to 13.

Colors: Most colors
To optimize hide and color development, always use the recommended P-Shade primer

Coverage: 350-400 sq ft/gal
@ 4.0 mils wet; 1.5 mils dry

Drying Time, @ 77°F, 50% RH:

Touch: 1 hour
Recoat: 4 hours

Drying and recoat times are temperature, humidity, and film thickness dependent.

Flash Point: N/A

Finish: 35-45 units @ 60°

Tinting with CCE:

Base	oz/gal	Strength
Extra White	0-6	Sher-Color
Deep Base	4-12	Sher-Color
Ultra-deep	10-14	Sher-Color

Vehicle Type: 100% Acrylic
Extra White A76W00051

VOC (less exempt solvents):
<50 g/L; <0.42 lb/gal

As per 40 CFR 59.406 and SOR/2009-264, s.12

Volume Solids: 38 ± 2%

Weight Solids: 50 ± 2%

Weight per Gallon: 10.16 lb

Mildew Resistant

This coating contains agents which inhibit the growth of mildew on the surface of this coating film.

SPECIFICATIONS

Apply 2 topcoats of Solo Semi-Gloss directly over existing properly prepared, interior or exterior coatings, or new interior bare drywall, plaster (cured with a pH of less than 13), masonry (cured with a pH of less than 13) and non-bleeding wood.

Interior

Drywall

Self-prime using 2 cts. of Solo Semi-Gloss, or
1 ct. ProMar 200 Zero VOC Primer

Plaster

Self-prime using 2 cts. of Solo Semi-Gloss, or
1 ct. Premium Wall & Wood Primer

Wood

Self-prime using 2 cts. of Solo Semi-Gloss, or
1 ct. Premium Wall & Wood Primer

Interior & Exterior

Aluminum & Galvanized Steel

(if needed)
1 ct. Pro Industrial Pro-Cryl Primer

Block

1 ct. PrepRite Block Filler

Masonry, Cement, Stucco

1 ct. Loxon Concrete & Masonry Primer

Steel

1 ct. Pro Industrial Pro-Cryl Primer

Exterior

Wood, Composition Board

1 ct. Exterior Oil-Based Wood Primer or
Exterior Latex Wood Primer

Plywood

1 ct. Exterior Latex Wood Primer

Other primers may be appropriate.

When repainting involves a drastic color change, a coat of primer will improve the hiding performance of the topcoat color.

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at **1-800-424-LEAD** (in US) or contact your local health authority.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with the appropriate primer/sealer. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

Aluminum and Galvanized Steel

Wash to remove any oil, grease, or other surface contamination. All corrosion must be removed with sandpaper, wire brush, or other abrading method.

Steel

Rust and mill scale must be removed using sandpaper, wire brush, or other abrading method. Bare steel must be primed the same day as cleaned

Drywall

Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.



101.88

SOLO[®]

100% Acrylic Interior/Exterior Semi-Gloss A76 Series

<u>SURFACE PREPARATION</u>	<u>APPLICATION</u>	<u>CAUTIONS</u>
<p>Masonry, Concrete, Block- All new surfaces must be cured at least 7 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. Repair cracks, voids, and other holes with an elastomeric patch or sealant.</p> <p>Plaster- All new surfaces must be cured at least 7 days. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.</p> <p>Vinyl- Clean the surface thoroughly by scrubbing with warm, soapy water. Rinse thoroughly.</p> <p>Wood- Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.</p> <p>Exterior: Knots and some woods, such as redwood and cedar, contain a high amount of tannin, a colored wood extract. If applied to these bare woods, it may show some staining. If staining persists, spot prime severe areas with 1 coat of Exterior Oil-Based Wood Primer prior to using.</p> <p>Mildew- Prior to attempting to remove mildew, it is always recommended to test any cleaner on a small, inconspicuous area prior to use. Bleach and bleaching type cleaners may damage or discolor existing paint films. Bleach alternative cleaning solutions may be advised. Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.</p> <p>Caulking- Gaps between walls, ceilings, crown moldings, and other interior trim can be filled with the appropriate caulk after priming the surface.</p>	<p>Apply at temperatures above 50°F. No reduction needed.</p> <p>Brush Use a nylon/polyester brush.</p> <p>Roller Use a 1/4" - 1/2" nap synthetic cover.</p> <p>Spray—Airless Pressure 2000 psi Tip015"-.021" Reduction Up to 1 pint per gallon</p> <p><u>CLEANUP INFORMATION</u></p> <p>Clean spills, spatters, hands and tools immediately with soap and warm water. After cleaning, flush spray equipment with compliant clean up solvent to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using solvents. Do not pour unused contents down the drain. Consult with local authorities for method of disposal and recycling.</p>	<p>Non-photochemically reactive. Protect from freezing.</p> <p>Before using, carefully read CAUTIONS on label.</p> <p>HOTW 05/11/2016 A76W00051 15 15 KOR, SP, FRC,Viet</p> <p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative or visit www.paintdocs.com to obtain the most current version of the PDS and/or an SDS.</p>



**SHERWIN
WILLIAMS®**

102.40

DURACRAFT® Exterior Latex Flat

C01W00251 Extra White
C01W00253 Deep Base
C01T00254 Ultradeep Base

As of 10/04/2017, Complies with:			
OTC	Yes	LEED® 09 NC CI	N/A
OTC Phase II	Yes	LEED® 09 CS	N/A
SCAQMD	Yes	LEED® v4 Emissions	N/A
CARB	Yes	LEED® v4 VOC	Yes
CARB SCM2007	Yes		
Canada	Yes	MPI	

CHARACTERISTICS

DuraCraft Exterior Latex is a good commercial quality exterior finish. **DuraCraft** is recommended for use on aluminum, vinyl, and wood siding, clapboard, shakes, shingles, plywood, masonry, cementitious board, and metal. **DuraCraft Exterior Latex** can be applied down to a surface and air temperature of 35°F.

Color: Most colors
To optimize hide and color development, always use the recommended P-Shadow primer

Coverage: 350 - 400 sq ft/gal
@ 4 mils wet; 1.2 mils dry

Drying Time, @ 50% RH:
@ 35-45°F @ 45°F+

Touch: 2 hour 2 hours
Recoat: 24-48 hours 4 hours

Drying and recoat times are temperature, humidity, and film thickness dependent

Finish: 0-5 units @ 85°

Tinting with CCE:

Base	oz/gal	Strength
Extra White	0-6	SherColor
Deep Base	4-12	SherColor
Ultradeep	10-12	SherColor

Vehicle Type: 100% Acrylic

C01W00251

(may vary by color)

VOC (less exempt solvents):

<50 g/L; <0.42 lb/gal

As per 40 CFR 59.406 and SOR/2009-264, s.12

Volume Solids: 31 ± 2%

Weight Solids: 47 ± 2%

Weight per Gallon: 10.82 lb

Flash Point: N/A

WVP Perms (US) 37.37

grains/(hr ft² in Hg)

Mildew Resistant

This coating contains agents which inhibit the growth of mildew on the surface of this coating film.

SPECIFICATIONS

Standard latex primers cannot be used below 50°F. See specific primer label for that product's application conditions.

Aluminum & Aluminum Siding¹

2 cts. DuraCraft Exterior Latex
Concrete Block, CMU, Split face Block

1 ct. Loxon Block Surfer
2 cts. DuraCraft Exterior Latex

Brick

1 ct. Loxon Conditioner²
2 cts. DuraCraft Exterior Latex

Cement Composition Siding/Panels

1 ct. Loxon Concrete & Masonry Primer²
or Loxon Conditioner²

2 cts. DuraCraft Exterior Latex

Galvanized Steel¹

2 cts. DuraCraft Exterior Latex

Stucco, Cement, Concrete

1 ct. Loxon Concrete & Masonry Primer²

2 cts. DuraCraft Exterior Latex

Plywood

1 ct. Exterior Latex Wood Primer

2 cts. DuraCraft Exterior Latex

Vinyl Siding*

2 cts. DuraCraft Exterior Latex

Wood

1 ct. Exterior Oil-Based Wood Primer

2 cts. DuraCraft Exterior Latex

¹ On large expanses of metal siding, the air, surface, and material temperatures must be 50°F or higher.

² Not for use at temperatures under 50°F. See specific primer label for that product's application conditions.

Other primers may be appropriate.

When repainting involves a drastic color change, a coat of primer will improve the hiding performance of the topcoat color.

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at **1-800-424-LEAD** (in US) or contact your local health authority.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Scrape and sand peeled or checked paint to a sound surface. Sand glossy surfaces dull. Seal stains from water, smoke, ink, pencil, grease, etc. with the appropriate primer/sealer. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

Aluminum and Galvanized Steel

Wash to remove any oil, grease, or other surface contamination. All corrosion must be removed with sandpaper, wire brush, or other abrading method.

Caulking

Gaps between windows, doors, trim, and other through-wall openings can be filled with the appropriate caulk after priming the surface.

Cement Composition Siding/Panels

Remove all dirt, dust, grease, oil, loose particles, laitance, foreign material, and peeling or defective coatings. Allow the surface to dry thoroughly. If the surface is new, test it for pH, if the pH is higher than 9, prime with Loxon Concrete & Masonry Primer.



102.40

DURACRAFT®

Exterior Latex Flat

C01W00251 Extra White
C01W00253 Deep Base
C01T00254 Ultradeep Base

SURFACE PREPARATION	SURFACE PREPARATION	CAUTIONS
<p>Masonry, Concrete, Cement, Block All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with Loxon Concrete & Masonry Primer. Cracks, voids, and other holes should be repaired with an elastomeric patch or sealant.</p> <p>Steel Rust and mill scale must be removed using sandpaper, wire brush, or other abrading method. Bare steel must be primed the same day as cleaned.</p> <p>Stucco Remove any loose stucco, efflorescence, or laitance. Allow new stucco to cure at least 30 days before painting. If painting cannot wait 30 days, allow the surface to dry 7 days and prime with Loxon Concrete & Masonry Primer. Repair cracks, voids, and other holes with an elastomeric patch or sealant.</p> <p>*Vinyl or other PVC Building Products Clean the surface thoroughly by scrubbing with warm, soapy water. Rinse thoroughly, prime with appropriate white primer. Do not paint vinyl with any color darker than the original color. Do not paint vinyl with a color having a Light Reflective Value (LRV) of less than 56. Painting with darker colors lower than an LRV of 56 may cause vinyl to warp. Follow all painting guidelines of the vinyl manufacturer when painting. Only paint properly installed vinyl siding. Deviating from the manufacturer's painting guidelines may cause the warranty to be voided.</p> <p>Wood, Plywood, Composition Board Clean the surface thoroughly then sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth. All patched areas must be primed. Knots and some woods, such as redwood and cedar, contain a high amount of tannin, a colored wood extract. If applied to these bare woods, it may show some staining. If staining persists, spot prime severe areas with 1 coat of Exterior Oil-Based Wood Primer prior to using.</p>	<p>Mildew Prior to attempting to remove mildew, it is always recommended to test any cleaner on a small, inconspicuous area prior to use. Bleach and bleaching type cleaners may damage or discolor existing paint films. Bleach alternative cleaning solutions may be advised. Mildew may be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.</p> <p>APPLICATION When the air temperature is at 35°F, substrates may be colder; prior to painting, check to be sure the air, surface, and material temperature are above 35°F and at least 5°F above the dew point. Avoid using if rain or snow is expected within 2-3 hours.</p> <p>Do not apply at air or surface temperatures below 35°F or when air or surface temperatures may drop below 35°F within 48 hours.</p> <p>No reduction necessary.</p> <p>Brush Use a nylon/polyester brush.</p> <p>Roller Use a 3/8" - 3/4" nap synthetic cover.</p> <p>Spray—Airless Pressure..... 2000 psi Tip..... .015"-.019"</p>	<p>For exterior use only. Protect from freezing. Non-photochemically reactive.</p> <p>Before using, carefully read CAUTIONS on label.</p> <p>HOTW 10/04/2017 C01W00251 14 39 KOR, SP, FRC</p> <p>CLEANUP INFORMATION Clean spills, spatters, hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with a compliant cleanup solvent to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using solvents.</p> <p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative or visit www.paintdocs.com to obtain the most current version of the PDS and/or an SDS.</p>

ProMar® 400 Zero V.O.C. Interior Latex Flat

B30W04651 Extra White, B30W04653 Deep Base



**SHERWIN
WILLIAMS®**

CHARACTERISTICS

ProMar 400 Zero V.O.C. Interior Latex is a durable, professional quality, interior vinyl acrylic finish for use on walls, ceilings, and trim of primed plaster, wallboard, wood, masonry, and primed metal.

Color: Most Colors

To optimize hide and color development, always use the recommended P-Shadow primer

Coverage: 350-400 sq.ft.per gallon
@ 4 mils wet;
1.2 mils dry

Drying Time, @ 77°F, 50% RH:

Touch: 1 Hour

Recoat: 4 Hours

Drying and recoat times are temperature, humidity, and film thickness dependent

Finish: 0-5 units @ 85°

Tinting with CCE only:

Base:	oz. per gallon	Strength:
Extra White	0-6	SherColor
Deep Base	4-12	SherColor

Extra White B30W04651

(may vary by color)

V.O.C. (less exempt solvents):

less than 50 grams per litre; 0.42 lbs. per gallon
As per 40 CFR 59.406

Volume Solids: 29 ± 2%

Weight Solids: 48 ± 2%

Weight per Gallon: 11.25 lbs

Flash Point: N/A

Vehicle Type: Vinyl Acrylic

Shelf Life: 36 months unopened

WVP Perms (US): 25.5 grains/(hr ft² in Hg)

COMPLIANCE

As of 09/05/2019, Complies with:

OTC	Yes
OTC Phase II	Yes
SCAQMD	Yes
CARB	Yes
CARB SCM 2007	Yes
Canada	Yes
LEED® v4 & v4.1 Emissions	Yes
LEED® v4 & v4.1 V.O.C.	Yes
EPD-NSF® Certified	Yes
MIR-Product Lens Certified	No
MPI®	No

APPLICATION

Apply at temperatures above 50°F.
No reduction needed.

Brush:

Use a nylon/polyester brush.

Roller:

Use a 3/8 to 3/4 inch nap synthetic cover.

Spray—Airless

Pressure 2000 p.s.i.

Tip .017-.021 inch

APPLICATION TIPS

Make sure product is completely agitated (mechanically or manually) before use.

Priming and application of two coats at the recommended film thickness can help where hiding of a previous coating or application to new drywall is a factor.

Using the same method of application and batch to touch up with as that originally used will help improve touch up.

When original application was by spray, preconditioning of touch up paint by running it through the spray tip will help touch up appearance.

SPECIFICATIONS

Block:

1 coat PrepRite Block Filler*
2 coats ProMar 400 Zero V.O.C. Interior Latex

Drywall:

1 coat ProMar 400 Zero V.O.C. Latex Primer
2 coats ProMar 400 Zero V.O.C. Interior Latex

Masonry:

1 coat Loxon Concrete & Masonry Primer*
2 coats ProMar 400 Zero V.O.C. Interior Latex

Plaster:

1 coat Loxon Concrete & Masonry Primer*
2 coats ProMar 400 Zero V.O.C. Interior Latex

Wood:

1 coat Premium Wall & Wood Primer*
2 coats ProMar 400 Zero V.O.C. Interior Latex

*These primers contain less than 50 grams per litre V.O.C.

Other primers may be appropriate.

When repainting involves a drastic color change, a coat of primer will improve the hiding performance of the topcoat color.

ProMar® 400 Zero V.O.C. Interior Latex Flat

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (**NIOSH** approved) and proper containment and cleanup. For more information, call the National Lead Information Center at **1-800-424-LEAD** (in US) or contact your local health authority.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with the appropriate primer/sealer. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

Caulking:

Gaps between walls, ceilings, crown moldings, and other interior trim can be filled with the appropriate caulk after priming the surface.

Drywall:

Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.

Masonry, Concrete, Cement, Block:

All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with Loxon Concrete & Masonry Primer.

SURFACE PREPARATION

Mildew:

Prior to attempting to remove mildew, it is always recommended to test any cleaner on a small, inconspicuous area prior to use. Bleach and bleaching type cleaners may damage or discolor existing paint films. Bleach alternative cleaning solutions may be advised. Mildew may be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

Plaster:

Bare plaster must be cured and hard. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.

Wood:

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.

CAUTIONS

For interior use only
Protect from freezing.
Non-photochemically reactive.

Before using, carefully read **CAUTIONS on label**

CRYSTALLINE SILICA Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (**NIOSH** approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (**NIOSH** approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. **FIRST AID:** In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. **DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE.** Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. **WARNING:** This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. **DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.**

HOTW 09/05/2019 B30W04651 23 00
FRC,SP

CLEANUP INFORMATION

Clean spills, spatters, hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with compliant cleanup solvent to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using solvents.



**SHERWIN
WILLIAMS®**

102.41

DURACRAFT® Exterior Latex Satin

C07W00251 Extra White

As of 03/14/2018, Complies with:			
OTC	Yes	LEED® 09 NC CI	N/A
OTC Phase II	Yes	LEED® 09 CS	N/A
SCAQMD	Yes	LEED® v4 Emissions	N/A
CARB	Yes	LEED® v4 VOC	Yes
CARB SCM2007	Yes		
Canada	Yes	MPI	

CHARACTERISTICS

DuraCraft Exterior Latex is a good commercial quality exterior finish.

DuraCraft Exterior Latex is recommended for use on aluminum, vinyl, and wood siding, clapboard, shakes, shingles, plywood, masonry, cementitious board, and metal.

DuraCraft Exterior Latex can be applied down to a surface and air temperature of 35°F.

Color: Most colors

To optimize hide and color development, always use the recommended P-Shadow primer

Coverage: 350 - 400 sq ft/gal
@ 4 mils wet; 1.3 mils dry

Drying Time, @ 50% RH:
@ 35-45°F @ 45°F+

Touch: 2 hour 2 hours
Recoat: 24-48 hours 4 hours

Drying and recoat times are temperature, humidity, and film thickness dependent

Finish: 10-20 units @ 60°

Tinting with CCE:

Base	oz/gal	Strength
Extra White	0-6	SherColor

Vehicle Type: 100% Acrylic

C07W00251

(may vary by color)

VOC (less exempt solvents):

<50 g/L; <0.42 lb/gal

As per 40 CFR 59.406 and SOR/2009-264, s.12

Volume Solids: 33 ± 2%

Weight Solids: 43 ± 2%

Weight per Gallon: 9.85 lb

Flash Point: N/A

WVP Perms (US) 27.25
grains/(hr ft² in Hg)

Mildew Resistant

This coating contains agents which inhibit the growth of mildew on the surface of this coating film.

SPECIFICATIONS

Standard latex primers cannot be used below 50°F. See specific primer label for that product's application conditions.

Aluminum & Aluminum Siding¹

2 cts. DuraCraft Exterior Latex
Concrete Block, CMU, Split face Block

1 ct. Loxon Block Surfer
2 cts. DuraCraft Exterior Latex

Brick

1 ct. Loxon Conditioner²
2 cts. DuraCraft Exterior Latex

Cement Composition Siding/Panels

1 ct. Loxon Concrete & Masonry Primer²
or Loxon Conditioner²

2 cts. DuraCraft Exterior Latex

Galvanized Steel¹

2 cts. DuraCraft Exterior Latex

Stucco, Cement, Concrete

1 ct. Loxon Concrete & Masonry Primer²

2 cts. DuraCraft Exterior Latex

Plywood

1 ct. Exterior Latex Wood Primer

2 cts. DuraCraft Exterior Latex

Vinyl Siding*

2 cts. DuraCraft Exterior Latex

Wood

1 ct. Exterior Oil-Based Wood Primer

2 cts. DuraCraft Exterior Latex

¹ On large expanses of metal siding, the air, surface, and material temperatures must be 50°F or higher.

² Not for use at temperatures under 50°F. See specific primer label for that product's application conditions.

Other primers may be appropriate.

When repainting involves a drastic color change, a coat of primer will improve the hiding performance of the topcoat color.

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at **1-800-424-LEAD** (in US) or contact your local health authority.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Scrape and sand peeled or checked paint to a sound surface. Sand glossy surfaces dull. Seal stains from water, smoke, ink, pencil, grease, etc. with the appropriate primer/sealer. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

Aluminum and Galvanized Steel

Wash to remove any oil, grease, or other surface contamination. All corrosion must be removed with sandpaper, wire brush, or other abrading method.

Caulking

Gaps between windows, doors, trim, and other through-wall openings can be filled with the appropriate caulk after priming the surface.

Cement Composition Siding/Panels

Remove all dirt, dust, grease, oil, loose particles, laitance, foreign material, and peeling or defective coatings. Allow the surface to dry thoroughly. If the surface is new, test it for pH, if the pH is higher than 9, prime with Loxon Concrete & Masonry Primer.



102.41

DURACRAFT[®]

Exterior Latex Satin

C07W00251 Extra White

SURFACE PREPARATION

Masonry, Concrete, Cement, Block

All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with Loxon Concrete & Masonry Primer. Cracks, voids, and other holes should be repaired with an elastomeric patch or sealant.

Steel

Rust and mill scale must be removed using sandpaper, wire brush, or other abrading method. Bare steel must be primed the same day as cleaned.

Stucco

Remove any loose stucco, efflorescence, or laitance. Allow new stucco to cure at least 30 days before painting. If painting cannot wait 30 days, allow the surface to dry 7 days and prime with Loxon Concrete & Masonry Primer. Repair cracks, voids, and other holes with an elastomeric patch or sealant.

***Vinyl or other PVC Building Products**

Clean the surface thoroughly by scrubbing with warm, soapy water. Rinse thoroughly, prime with appropriate white primer. Do not paint vinyl with any color darker than the original color. Do not paint vinyl with a color having a Light Reflective Value (LRV) of less than 56. Painting with darker colors lower than an LRV of 56 may cause vinyl to warp. Follow all painting guidelines of the vinyl manufacturer when painting. Only paint properly installed vinyl siding. Deviating from the manufacturer's painting guidelines may cause the warranty to be voided.

Wood, Plywood, Composition Board

Clean the surface thoroughly then sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth. All patched areas must be primed. Knots and some woods, such as redwood and cedar, contain a high amount of tannin, a colored wood extract. If applied to these bare woods, it may show some staining. If staining persists, spot prime severe areas with 1 coat of Exterior Oil-Based Wood Primer prior to using.

SURFACE PREPARATION

Mildew

Prior to attempting to remove mildew, it is always recommended to test any cleaner on a small, inconspicuous area prior to use. Bleach and bleaching type cleaners may damage or discolor existing paint films. Bleach alternative cleaning solutions may be advised.

Mildew may be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

APPLICATION

When the air temperature is at 35°F, substrates may be colder; prior to painting, check to be sure the **air, surface, and material temperature** are above 35°F and at least 5°F above the dew point. Avoid using if rain or snow is expected within 2-3 hours.

Do not apply at air or surface temperatures below 35°F or when air or surface temperatures may drop below 35°F within 48 hours.

No reduction necessary.

Brush

Use a nylon/polyester brush.

Roller

Use a 3/8" - 3/4" nap synthetic cover.

Spray—Airless

Pressure 2000 psi
Tip015"-.019"

CAUTIONS

For exterior use only.
Protect from freezing.
Non-photochemically reactive.

Before using, carefully read **CAUTIONS** on label.

HOTW 03/14/2018 C07W00251 13 40

KOR,SP,FRC

CLEANUP INFORMATION

Clean spills, spatters, hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with a compliant cleanup solvent to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using solvents.

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative or visit www.paintdocs.com to obtain the most current version of the PDS and/or an SDS.



**SHERWIN
WILLIAMS®**

101.56

PROPERTY SOLUTION™

Interior Latex Eg-Shel

B20W03050 White
B20W03053 Deep Base

As of 05/08/2017, Complies with:			
OTC	Yes	LEED® 09 NC, CI, CS	Yes
OTC Phase II	Yes	LEED® 09 H	Yes
SCAQMD	Yes	LEED® v4 Emissions	No
CARB	Yes	LEED® v4 VOC	Yes
CARB SCM 2007	Yes		
Canada	Yes	MPI	

CHARACTERISTICS

Property Solution™ Interior Latex is designed for the new construction, commercial and multi-family housing markets. It provides good hiding and great touch-up.

Property Solution™ Interior Latex is ideal for use in occupied buildings with little disruption to other tenants.

Color: Many colors
To optimize hide and color development, always use the recommended P-Shadow primer

Coverage: 350 - 400 sq ft/gal
@ 4.0 mils wet; 1.6 mils dry

Drying Time, @ 77°F, 50% RH:

Touch: 1 hour

Recoat: 4 hours

Drying and recoat times are temperature, humidity, and film thickness dependent

Flash Point: N/A

Finish: 10-20 units @ 85°

Tinting with CCE:

Base	oz/gal	Strength
-------------	---------------	-----------------

White	0-4	SherColor
-------	-----	-----------

Deep Base	4-12	SherColor
-----------	------	-----------

Vehicle Type: Vinyl Acrylic

White B20W03050

VOC (less exempt solvents):

<50 g/L; <0.42 lb/gal

As per 40 CFR 59.406 and SOR/2009-264, s.12

Volume Solids: 40 ± 2%

Weight Solids: 55 ± 2%

Weight per Gallon: 11.18 lb

SPECIFICATIONS

Block

- 1 ct. Loxon Block Surfer
- 2 cts. Property Solution Interior Latex

Drywall

- 1 ct. ProMar 400 Latex Primer
- 2 cts. Property Solution Interior Latex

Masonry

- 1 ct. Loxon Concrete & Masonry Primer
- 2 cts. Property Solution Interior Latex

Plaster

- 1 ct. Premium Wall and Wood Primer
- 2 cts. Property Solution Interior Latex

Wood

- 1 ct. Premium Wall and Wood Primer
- 2 cts. Property Solution Interior Latex

Other primers may be appropriate.

When repainting involves a drastic color change, a coat of primer will improve the hiding performance of the topcoat color.

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at **1-800-424-LEAD** (in US) or contact your local health authority.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with the appropriate primer/sealer. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

Drywall

Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.

Masonry, Concrete, Cement, Block

All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with Loxon Concrete & Masonry Primer.



101.56

PROPERTY SOLUTION™

Interior Latex Eg-Shel

B20W03050 White
B20W03053 Deep Base

<u>SURFACE PREPARATION</u>	<u>APPLICATION</u>	<u>CAUTIONS</u>
<p>Plaster Bare plaster must be cured and hard. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.</p> <p>Wood Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.</p> <p>Mildew Prior to attempting to remove mildew, it is always recommended to test any cleaner on a small, inconspicuous area prior to use. Bleach and bleaching type cleaners may damage or discolor existing paint films. Bleach alternative cleaning solutions may be advised. Mildew may be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.</p> <p>Caulking Gaps between walls, ceilings, crown moldings, and other interior trim can be filled with the appropriate caulk after priming the surface.</p>	<p>Apply at temperatures above 50°F. No reduction needed.</p> <p>Brush Use a nylon/polyester brush.</p> <p>Roller Use a 1/4" - 3/4" nap synthetic cover.</p> <p>Spray-Airless Pressure2000 psi Tip......017"-.021"</p> <p><u>CLEANUP INFORMATION</u></p> <p>Clean spills, spatters, hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with compliant cleanup solvent to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using solvents.</p>	<p>For interior use only. Protect from freezing. Non-photochemically reactive.</p> <p>Before using, carefully read CAUTIONS on label</p> <p>HOTW 05/08/2017 B20W03050 19 35 FRC</p> <p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative or visit www.paintdocs.com to obtain the most current version of the PDS and/or an SDS.</p>

ProMar® 400 Zero V.O.C. Interior Latex Low Sheen

B24W04651 Extra White, B24W04653 Deep Base


**SHERWIN
WILLIAMS®**

CHARACTERISTICS

ProMar 400 Zero V.O.C. Interior Latex is a durable, professional quality, interior vinyl acrylic finish for use on walls, ceilings, and trim of primed plaster, wallboard, wood, masonry, and primed metal.

Color: Most Colors

To optimize hide and color development, always use the recommended P-Shadow primer

Coverage: 350-400 sq.ft.per gallon
@ 4 mils wet;
1.5 mils dry

Drying Time, @ 77°F, 50% RH:

Touch: 1 Hour

Recoat: 4 Hours

Drying and recoat times are temperature, humidity, and film thickness dependent

Finish: Low Sheen

Tinting with CCE only:

Base:	oz. per gallon	Strength:
Extra White	0-6	SherColor
Deep Base	4-12	SherColor

Extra White B24W04651

(may vary by color)

V.O.C. (less exempt solvents):

less than 50 grams per litre; 0.42 lbs. per gallon
As per 40 CFR 59.406

Volume Solids: 38 ± 2%

Weight Solids: 52 ± 2%

Weight per Gallon: 10.92 lbs

Flash Point: N/A

Vehicle Type: Vinyl Acrylic

Shelf Life: 36 months unopened

WVP Perms (US): 8.3 grains/(hr ft² in Hg)

COMPLIANCE

As of 09/05/2019, Complies with:

OTC	Yes
OTC Phase II	Yes
SCAQMD	Yes
CARB	Yes
CARB SCM 2007	Yes
Canada	Yes
LEED® v4 & v4.1 Emissions	Yes
LEED® v4 & v4.1 V.O.C.	Yes
EPD-NSF® Certified	Yes
MIR-Product Lens Certified	No
MPI®	No

APPLICATION

Apply at temperatures above 50°F.
No reduction needed.

Brush:

Use a nylon/polyester brush.

Roller:

Use a 3/8 to 3/4 inch nap synthetic cover.

Spray—Airless

Pressure 2000 p.s.i.

Tip .017-.021 inch

APPLICATION TIPS

Make sure product is completely agitated (mechanically or manually) before use.

Priming and application of two coats at the recommended film thickness can help where hiding of a previous coating or application to new drywall is a factor.

Using the same method of application and batch to touch up with as that originally used will help improve touch up.

When original application was by spray, preconditioning of touch up paint by running it through the spray tip will help touch up appearance.

SPECIFICATIONS

Block:

1 coat PrepRite Block Filler*
2 coats ProMar 400 Zero V.O.C. Interior Latex

Drywall:

1 coat ProMar 400 Zero V.O.C. Latex Primer
2 coats ProMar 400 Zero V.O.C. Interior Latex

Masonry:

1 coat Loxon Concrete & Masonry Primer*
2 coats ProMar 400 Zero V.O.C. Interior Latex

Plaster:

1 coat Loxon Concrete & Masonry Primer*
2 coats ProMar 400 Zero V.O.C. Interior Latex

Wood:

1 coat Premium Wall & Wood Primer*
2 coats ProMar 400 Zero V.O.C. Interior Latex

*These primers contain less than 50 grams per litre V.O.C.

Other primers may be appropriate.

When repainting involves a drastic color change, a coat of primer will improve the hiding performance of the topcoat color.

ProMar® 400 Zero V.O.C. Interior Latex Low Sheen

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at **1-800-424-LEAD** (in US) or contact your local health authority.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with the appropriate primer/sealer. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

Caulking:

Gaps between walls, ceilings, crown moldings, and other interior trim can be filled with the appropriate caulk after priming the surface.

Drywall:

Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.

Masonry, Concrete, Cement, Block:

All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with Loxon Concrete & Masonry Primer.

SURFACE PREPARATION

Mildew:

Prior to attempting to remove mildew, it is always recommended to test any cleaner on a small, inconspicuous area prior to use. Bleach and bleaching type cleaners may damage or discolor existing paint films. Bleach alternative cleaning solutions may be advised. Mildew may be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

Plaster:

Bare plaster must be cured and hard. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.

Wood:

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.

CAUTIONS

For interior use only
Protect from freezing.
Non-photochemically reactive.

Before using, carefully read **CAUTIONS on label**

CRYSTALLINE SILICA Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. **FIRST AID:** In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. **DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE.** Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. **WARNING:** This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. **DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.**

HOTW 09/05/2019 B24W04651 18 00
FRC,SP

CLEANUP INFORMATION

Clean spills, spatters, hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with compliant cleanup solvent to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using solvents.


**SHERWIN
WILLIAMS.**

As of 02/14/2012, Complies with:

VOCs Canada	Yes
CAGBC Cl V1.0	Yes
CAGBC NC 09	Yes
MPI # Gloss	114, 154
MPI# Semi-Gloss	141, 147, 153

ALL SURFACE ENAMEL HP

100% Acrylic Interior/Exterior

A42 Series	Gloss
A41 Series	Semi-Gloss
A43 Series	Eg-Shel

CHARACTERISTICS

All Surface Enamel HP is designed for use on a variety of interior and exterior substrates including wood, metal, drywall and masonry. This high quality coating provides excellent resistance to weather and sunlight, maintaining its gloss and color. The exceptional durability also allows it to be used on doors, windows, baseboards, trim and other high traffic areas.

Color: Many Colors

Coverage: 350 - 400 sq ft/gal
@ 4.0 mils wet; 1.4 mils dry

Drying Time, @ 25°C (77°F), 50% RH:
temperature and humidity dependent

Touch: 30 minutes

Recoat: 5 hours

Flash Point: N/A

Finish: Gloss, Semi-Gloss, Eg-Shel

Tinting with CCE:

Base	oz/gal	Strength
Extra White	0-4	100%
Deep Base	8-12	100%
Ultradeep Base	8-12	100%

Vehicle Type: Acrylic

A41WQ8051 (Semi-Gloss)

VOC (less exempt solvents):

<50 g/L; 0.42 lb/gal

As per 40 CFR 59.406 and SOR/2009-264, s. 12

Volume Solids: 36 ± 2%

Weight Solids: 45 ± 2%

Weight per Gallon: 9.5 lb/gal ±2%

SPECIFICATIONS

Aluminum

2 cts. All Surface Enamel HP Acrylic

Drywall, interior

1 ct. Premium Wall & Wood Primer

2 cts. All Surface Enamel HP Acrylic

Galvanized Steel

2 cts. All Surface Enamel HP Acrylic

Masonry, Concrete, Cement, Block

1 ct. PrepRite Block Filler (optional)

or Loxon Masonry Primer

2 cts. All Surface Enamel HP Acrylic

Steel

2 cts. All Surface Enamel HP Acrylic

Wood, interior

1 ct. Premium Wall & Wood Primer

2 cts. All Surface Enamel HP Acrylic

Wood, exterior

1 ct. Exterior Latex Wood Primer

2 cts. All Surface Enamel HP Acrylic

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call your local health authority.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. **Do not use hydrocarbon solvents for cleaning.** Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with the appropriate primer/sealer.

Aluminum and Galvanized Steel

Wash to remove any oil, grease, or other surface contamination using a water-based cleaner-degreaser. **Do not use hydrocarbon solvents for cleaning.** Remove all corrosion with sandpaper, steel wool, or other abrading method.

Drywall

Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.



ALL SURFACE ENAMEL HP

100% Acrylic Interior/Exterior

A42 Series	Gloss
A41 Series	Semi-Gloss
A43 Series	Eg-Shel

SURFACE PREPARATION

Masonry, Concrete, Cement, Block

All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with Loxon Masonry Primer.

Steel

Rust and mill scale must be removed using sandpaper, steel wool, or other abrading method. Bare steel must be primed the same day as cleaned.

Wood

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.

Mildew

Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

Caulking

Exterior gaps between windows, doors, trim, and other through-wall openings; and interior gaps between walls, ceilings, crown moldings, and other trim can be filled with the appropriate caulk after priming the surface.

APPLICATION

Apply at temperatures above 10°C, (50°F).

No reduction necessary.

Brush

Use a nylon/polyester brush

Roller

Use a 3/8" woven cover

Spray—Airless

Pressure 1500 psi

Tip017" - .021"

CLEANUP INFORMATION

Clean spills, spatters, hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

CAUTIONS

Protect from freezing.

Not for use on roofs, floors, or decks.

Do not use colorants formulated for interior use only on exterior surfaces.

LABEL CAUTIONS

Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.

HOTW 03/25/2011 A41WQ8051 08 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.